

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTa Product Testing
A.B.N 43 006 014 106
1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : TPM Distributors
48 Frankston-Dandenong Road
DANDENONG VIC 3175

Test Number : 20-002695
Issue Date : 7/07/2020
Print Date : 7/07/2020

Sample Description

Clients Ref : "Cotswold"
Cut pile tufted carpet
Colour : Grey
End Use : Flooring
Nominal Composition : 80% Wool, 20% Nylon
Nominal Mass per Unit Area/Density : 1350g/m²
Nominal Thickness : 9.5mm

**AS ISO 9239.1-2003
(Modified Guidance)**

Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source

Date of Sample Arrival 28/05/2020

Date Tested 03/07/2020

CHF Value	
Length	≤1.1 kW/m ²
Width	≤1.1 kW/m ²
HF-30 Value	
Length	1.8 kW/m ²
Width	≤1.1 kW/m ²
Smoke Value	
Length	237 %.min
Width	408 %.min

208076

44492

Page 1 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing	: Accreditation No.	983
- Mechanical Testing	: Accreditation No.	985
- Performance & Approvals Testing	: Accreditation No.	1356



Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTa Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTa Product Testing and AWTa Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTa Ltd.

APPROVED SIGNATORY

0204/11/06

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTa Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : TPM Distributors
48 Frankston-Dandenong Road
DANDENONG VIC 3175

Test Number : 20-002695
Issue Date : 7/07/2020
Print Date : 7/07/2020

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

Each specimen was loose laid over Dunlop Government Red underlay and 6mm thick fibre reinforced cement board and clamped prior to testing.

^ - NATA Accreditation does not cover the performance of this test.

208076

44492

Page 2 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing	: Accreditation No.	983
- Mechanical Testing	: Accreditation No.	985
- Performance & Approvals Testing	: Accreditation No.	1356



Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTa Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTa Product Testing and AWTa Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTa Ltd.

APPROVED SIGNATORY

0204/11/06

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR